


Spectrum Parameters

x:	0.1810	y:	0.0716		
u:	0.2070	v:	0.1229		
WD:	454.2 nm	WP:	390.9 nm		
HW:	12.3 nm	Purity:	84.003		
CCT:	100000 K	Ra:	36.8		
SDCM :	136.57	DUV :	-0.0860		
Ratio :	R%: 3.8	G%: 0.6	B%: 95.6		
Kred	5.67%	Kgreen	70.86%	Kblue	23.47%
R1:	58.0	R2:	75.4	R3:	18.0
R4:	13.5	R5:	53.8	R6:	8.1
R7:	51.0	R8:	16.9	R9:	-56.4
R10:	26.2	R11:	23.4	R12:	-75.9
R13:	57.7	R14:	55.5	R15:	62.2




Electrical parameters

Flux:	11.844 lm	E:	11.466 lm/w	P:	300.51 mw	
I:	315.0 mA	V:	3.28 V	P:	1.033 w	PF:


Memo:

Product Mode:	1	Item No:	1
Tester:	Y	Date:	2025-03-27 14:43
Temperature:	24 ()	Humidity:	60 (%)
Manufacturer:	ZVISION	organization:	杭州中为光电



Spectrum Parameters

x:	0.1813	y:	0.0703		
u:	0.2083	v:	0.1212		
WD:	453.5 nm	WP:	391.2 nm		
HW:	12.5 nm	Purity:	84.241		
CCT:	100000 K	Ra:	36.7		
SDCM:	137.21	DUV:	-0.0848		
Ratio:	R%: 3.7	G%: 0.5	B%: 95.8		
Kred	5.89%	Kgreen	70.49%	Kblue	23.61%
R1:	58.4	R2:	74.1	R3:	16.7
R4:	13.1	R5:	53.7	R6:	8.1
R7:	50.5	R8:	18.6	R9:	-48.8
R10:	22.9	R11:	22.8	R12:	-78.3
R13:	59.3	R14:	55.0	R15:	63.6



Electrical parameters

Flux:	12.982 lm	E:	11.201 lm/w	P:	328.22 mw		
I:	350.0 mA	V:	3.31 V	P:	1.159 w	PF:	

Memo:

Product Mode:	1	Item No:	2
Tester:	Y	Date:	2025-03-27 14:43
Temperature:	24 ()	Humidity:	60 (%)
Manufacturer:	ZVISION	organization:	杭州中为光电